



Thin, semi-infinite plane sample.



$$P = G \frac{V}{I}, \quad G = \frac{\pi}{\ln 2} t D_4 \left(\frac{L}{s} \right) F \left(\frac{t}{s}, \frac{L}{s} \right)$$

| L/s | $D_4 \left(\frac{L}{s} \right)$ |
|-------|----------------------------------|
| 0 | 0,5 |
| 0,1 | 0,5053 |
| 0,2 | 0,5205 |
| 0,3 | 0,5434 |
| 0,4 | 0,5714 |
| 0,5 | 0,6021 |
| 0,7 | 0,6645 |
| 1 | 0,7168 |
| 1,2 | 0,7905 |
| 1,5 | 0,8409 |
| 2 | 0,8951 |
| 2,5 | 0,9270 |
| 3 | 0,9468 |
| 4 | 0,9685 |
| 5 | 0,9793 |
| 7 | 0,9892 |
| 10 | 0,9946 |

